

**Synco Lube® " ...everywhere  
and no wear"!**



**SYNCO CHEMICAL CORPORATION**  
**vertreten durch:**

Pirola Groß- und Einzelhandel Import und Export  
GmbH

Ballertshofen 41

92283 Lauterhofen

+49 (0) 9189 4128976

e-mail: [info@synco-lube.com](mailto:info@synco-lube.com)

[www.synco-lube.com](http://www.synco-lube.com)



## KOMPATIBILITÄTSLISTE

Synco Lube® Silikon Dielektrikum Fett

Synco Lube® Silicone Dielectric Grease

<b>Polymer (Kunststoffe)</b> <small>Prüfung auf konstante Dehnung Zugfestigkeit</small>	<b>Bewertung</b>
Acrylonitrile Butadiene Styrene (ABS)	E
Cellulose acetate (CA)	E
Polyamide (PA) (Nylon)	E
Polycarbonate (PC)	E
Polyethylene (PE)	E
*ultra high molecular mass (PE-UHMW)	E
*low density (PE-LD)	E
Polyethylene-/polybutylenetherephthalat (PET / PBT)	E
Polyoxymethylene, Polyacetate (POM) (Delrin)	G
Polypropylene (PP)	E
Polyphenylene oxide (PPO)	E
Polyphenylene sulphide (PPS)	G
Polystyrene (PS)	E
Polytetrafluoroethylene (PTFE)	E
Polyurethane (PUR)	E
Polyvinylchloride (PVC)	E
Thermoplastic elastomer (TPE)	E
<b>Elastomere (Gummi / Kautschuk)</b>	<b>Bewertung</b>
Acrylic rubber (ACM)	E
Buna S	E
Butyl (IIR)	E
Polychloroprene rubber (CR)	E
Chlorosulphonated PE-rubber (CSM)	E
Ethylene-propylene-diene rubber (EPDM)	E
Fluorinated rubber (FKM)	E
Natural rubber (NR)	E
Neoprene	E
Nitrile (NBR)	E
Polyurethane (AU, EU)	E
Propylene-tetrafluoroethylene rubber (FPM, FEPM)	E
Styrene-butadiene rubber (SBR)	E
Silicone rubber (FMQ, PMQ, MQ, VMFQ, VMQ)	NC
Viton (FKM)	E
<b><u>Bewertungsschlüssel</u></b>	
E - Kompatibilität ausgezeichnet	
G - Kompatibilität gut	
NC - Nicht kompatibel	